













6 mm / Fine Porcelain Stoneware















E.N. 14411-ISO 13006 . Appendix G. Group B1a. UGL		Test method	Reference value	Declared value
	Barefoot slip resistance	DIN-EN-16165-ANNEX-A	-	18° ≤ α < 24° Cl. B Matte
	Slip resistance with shoes	DIN-EN-16165-ANNEX-B	-	6° ≤ α < 10° R9 Soft
	Slip resistance with shoes	DIN-EN-16165-ANNEX-B	-	10° ≤ α < 19° R10 Matte
	Release of hazardous substances	DM-1-2-2007-Reg-CE-1935-2004	Valore dichiarato per superfici gl con impieghi su piani di lavoro / Declared value for gl surfaces used on worktops / valeur déclarée Pour surfaces gl utilisées sur plans de travail / angegebenwert für Gl oberflächen zum gebrauch als arbeitsplatten / valor declarado Para acabados gl utilizados para superficies de trabajo / заявленное Значение для глазурированных поверхностей, с использованием на рабочих столах	CONFORME / CONFORMING / CONFORME / KONFORM / CONFORME / COOTBETCTBYET
	Maximum straightness deviation, in %, in relation to the corresponding production dimensions	ISO-10545-2	Squadrato ISO 13006 - ±0,3% (±0,8 mm)	± 0,1%
	Maximum right-angle deviation, in %, in relation to the corresponding production dimensions	ISO-10545-2	Squadrato ISO 13006 - ±0,3% (±1,5 mm)	± 0,2%
	Length and width: admitted deviation, in %, of the average size of each tile from the production dimensions	ISO-10545-2	Squadrato ISO 13006 - ±0,3% (±1 mm)	± 0,15%
	Flatness (centre curvature / edge curvature / warpage)	ISO-10545-2	Squadrato ISO 13006 - ±0,4% (±1,8 mm)	±0,2%
	Admitted deviation, in %, of the average thickness of each tile from the production dimensions	ISO-10545-2	Squadrato ISO 13006 - ±5% (±0,5 mm)	± 5%
	Surface quality	ISO-10545-2	Il 95% min delle piastrelle deve essere esente da difetti visibili / At least 95% of the tiles must be free from visible flaws / 95% min des carreaux ne doivent présenter aucun défaut visible / Mindestens 95% der Fliesen müssen frei von sichtbaren / mín. el 95% de las baldosas tiene que estar exento de defectos visibles	CONFORME / CONFORMING / CONFORME / KONFORM / CONFORME / COOTBETCTBYET
	Amount of water absorbed, in percentage	ISO-10545-3	E≤0,5%	average value 0,08%
	Bending strength in N/mm2	ISO-10545-4	>35 N/mm2	average value 52 N/mm2

	Breaking strength in N (thickness < 7,5 mm)	ISO-10545-4	≥700 Newton	average value 1350 N
	Resistance to deep abrasion of unglazed tiles	ISO-10545-6	<175 mm ³	average value 140 mm ³
	Thermal shock resistance	ISO-10545-9	Metodo di prova disponibile / Available testing method / Méthode d'essai disponible / Verfügbare Prüfmethode / Método de ensayo disponible	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Frost resistance	ISO-10545-12	Richiesta / Required / Requisite / Gefordert / Requerida	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Resistance to low concentrations of acids and alkali	ISO-10545-13	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	LA Matte
	Resistance to low concentrations of acids and alkali	ISO-10545-13	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	LB Soft
	Resistance to domestic chemicals and additives for swimming pools	ISO-10545-13	minimo / B minimum / B minimum / B mindestens / B minimo	A
	Resistance to staining	ISO-10545-14	-	Cl. 5













Note:

For optimal installation results, Florim recommends maintaining a joint of 2 mm 1/12" for single format installations and 3 mm 1/8" to combine mixed formats.

9 mm / Fine Porcelain Stoneware

	E.N. 14411-ISO 13006 . Appendix G. Group BIa. UGL	Test method	Reference value	Declared value
	Friction coefficient (slipperiness)	ANSI-A326.3	-	> 0,42 wet
	Pendulum friction test	BS-EN-16165- ANNEX-C	-	PTV > 36 wet slider 4S R+PTV
	Barefoot slip resistance	DIN-EN-16165- ANNEX-A	-	18° ≤ α < 24° Cl. B Matte
	Slip resistance with shoes	DIN-EN-16165- ANNEX-B	-	19° ≤ α < 27° R11 R+PTV
	Slip resistance with shoes	DIN-EN-16165- ANNEX-B	-	6° ≤ α < 10° R9 Soft
	Slip resistance with shoes	DIN-EN-16165- ANNEX-B	-	10° ≤ α < 19° R10 Canneté
	Slip resistance with shoes	DIN-EN-16165- ANNEX-B	-	10° ≤ α < 19° R10 Matte
	Admitted deviation, in %, of the average thickness of each tile from the production dimensions	ISO-10545-2	Squadrato ISO 13006 - ±5% (±0,5 mm)	± 5%
	Length and width: admitted deviation, in %, of the average size of each tile from the production dimensions	ISO-10545-2	Squadrato ISO 13006 - ±0,3% (±1 mm)	± 0,15%
	Surface quality	ISO-10545-2	Il 95% min delle piastrelle deve essere esente da difetti visibili / At least 95% of the tiles must be free from visible flaws / 95% min des carreaux ne doivent présenter aucun défaut visible / Mindestens 95% der Fliesen müssen frei von sichtbaren / mín. el 95% de las baldosas tiene que estar exento de defectos visibles	CONFORME / CONFORMING / CONFORME / KONFORM / CONFORME / COOTBETCTBYET
	Maximum right-angle deviation, in %, in relation to the corresponding production dimensions	ISO-10545-2	Squadrato ISO 13006 - ±0,3% (±1,5 mm)	± 0,2%
	Maximum straightness deviation, in %, in relation to the corresponding production dimensions	ISO-10545-2	Squadrato ISO 13006 - ±0,3% (±0,8 mm)	± 0,1%
	Flatness (centre curvature / edge curvature / warpage)	ISO-10545-2	Squadrato ISO 13006 - ±0,4% (±1,8 mm)	± 0,35%
	Amount of water absorbed, in percentage	ISO-10545-3	E≤0,5%	average value 0,08%

Breaking strength in N (thickness < 7,5















	mm)	ISO-10545-4	≥1300 Newton	average value 2200 N
	Bending strength in N/mm2	ISO-10545-4	>35 N/mm2	average value 50 N/mm2
	Resistance to deep abrasion of unglazed tiles	ISO-10545-6	<175 mm3	average value 140 mm3
	Thermal shock resistance	ISO-10545-9	Metodo di prova disponibile / Available testing method / Méthode d'essai disponible / Verfügbare Prüfmethode / Método de ensayo disponible	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Frost resistance	ISO-10545-12	Richiesta / Required / Requisite / Gefordert / Requerida	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Resistance to domestic chemicals and additives for swimming pools	ISO-10545-13	minimo / B minimum / B minimum / B mindestens / B minimo	A
	Resistance to high concentrations of acids and alkali	ISO-10545-13	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	HA Cannelé
	Resistance to low concentrations of acids and alkali	ISO-10545-13	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	LA R+PTV
	Resistance to low concentrations of acids and alkali	ISO-10545-13	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	LA Matte
	Resistance to high concentrations of acids and alkali	ISO-10545-13	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	HA Matte
	Resistance to low concentrations of acids and alkali	ISO-10545-13	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	LB Soft
	Resistance to low concentrations of acids and alkali	ISO-10545-13	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	LA Cannelé
	Resistance to high concentrations of acids and alkali	ISO-10545-13	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	HB Soft
	Resistance to staining	ISO-10545-14	-	Cl. 4





Note:

For optimal installation results, Florim recommends maintaining a joint of 2 mm 1/12" for single format installations and 3 mm 1/8" to combine mixed formats.

Copyright © 2025 Florim S.p.A. SB a socio unico.
Sede Legale: Via Canaletto 24, 41042 Fiorano Modenese.
Reg. Imprese di Modena Nr. 01265320364.
Capitale Sociale i.v. Euro 50.000.000 PI/CF 01265320364

20 mm / Fine Porcelain Stoneware

	E.N. 14411-ISO 13006 . Appendix G. Group BIa. UGL	Test method	Reference value	Declared value
	Friction coefficient (slipperiness)	ANSI-A326.3	-	>0,42 wet
	Pendulum friction test	BS-EN-16165- ANNEX-C	-	PTV > 36 wet slider 4S
	Barefoot slip resistance	DIN-EN-16165- ANNEX-A	-	24° ≤ α Cl. C
	Slip resistance with shoes	DIN-EN-16165- ANNEX-B	-	19° < α ≤ 27° R11
	Maximum straightness deviation, in %, in relation to the corresponding production dimensions	ISO-10545-2	Squadrato ISO 13006 - ±0,3% (±0,8 mm)	± 0,1%
	Length and width: admitted deviation, in %, of the average size of each tile from the production dimensions	ISO-10545-2	Squadrato ISO 13006 - ±0,3% (±1 mm)	± 0,15%
	Flatness (centre curvature / edge curvature / warpage)	ISO-10545-2	Squadrato ISO 13006 - ±0,4% (±1,8 mm)	± 0,35%
	Maximum right-angle deviation, in %, in relation to the corresponding production dimensions	ISO-10545-2	Squadrato ISO 13006 - ±0,3% (±1,5 mm)	± 0,2%
	Surface quality	ISO-10545-2	Il 95% min delle piastrelle deve essere esente da difetti visibili / At least 95% of the tiles must be free from visible flaws / 95% min des carreaux ne doivent présenter aucun défaut visible / Mindestens 95% der Fliesen müssen frei von sichtbaren / mín. el 95% de las baldosas tiene que estar exento de defectos visibles	CONFORME / CONFORMING / CONFORME / KONFORM / CONFORME / COOTBETCTBYET
	Admitted deviation, in %, of the average thickness of each tile from the production dimensions	ISO-10545-2	Squadrato ISO 13006 - ±5% (±0,5 mm)	± 5%
	Amount of water absorbed, in percentage	ISO-10545-3	E≤0,5%	average value 0,08%
	Bending strength in N/mm2	ISO-10545-4	>35 N/mm2	average value 52 N/mm2
	Resistance to deep abrasion of unglazed tiles	ISO-10545-6	<175 mm3	average value 140 mm3
	Thermal shock resistance	ISO-10545-9	Metodo di prova disponibile / Available testing method / Méthode d'essai disponible / Verfügbare Prüfmethode / Método de ensayo disponible	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ

	Frost resistance	ISO-10545-12	Richiesta / Required / Requisite / Gefordert / Requerida	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Resistance to low concentrations of acids and alkali	ISO-10545-13	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	LA
	Resistance to domestic chemicals and additives for swimming pools	ISO-10545-13	B minimo / B minimum / B minimum / B mindestens / B minimo	A
	Resistance to staining	ISO-10545-14	Metodo di prova disponibile / Available testing method / Méthode d'essai disponible / Verfügbare Prüfmethode / Método de ensayo disponible	Cl. 4

Note:

For optimal installation results, Florim recommends maintaining a joint of 2 mm 1/12" for single format installations and 3 mm 1/8" to combine mixed formats.

Copyright © 2025 Florim S.p.A. SB a socio unico.
 Sede Legale: Via Canaletto 24, 41042 Fiorano Modenese.
 Reg. Imprese di Modena Nr. 01265320364.
 Capitale Sociale i.v. Euro 50.000.000 PI/CF 01265320364