



























## 9 mm / Glazed Porcelain Stoneware

	E.N. 14411-ISO 13006 . Appendix G. Group Bla. GL	Test method	Reference value	Declared value
	Friction coefficient (slipperiness)	ANSI-A326.3	-	> 0,42 wet Matte
	Friction coefficient (slipperiness)	ANSI-A326.3	-	> 0,42 wet Grip
	Barefoot slip resistance	DIN-EN-16165- ANNEX-A	-	Cl. A+B Grip
	Slip resistance with shoes	DIN-EN-16165- ANNEX-B	-	R9 Matte
	Slip resistance with shoes	DIN-EN-16165- ANNEX-B	-	R11 Grip
	Length and width: admitted deviation, in %, of the average size of each tile from the production dimensions	ISO-10545-2	Squadro ISO 13006 - $\pm 0,3\%$ ( $\pm 1$ mm)	$\pm 0,15\%$
	Maximum right-angle deviation, in %, in relation to the corresponding production dimensions	ISO-10545-2	Squadro ISO 13006 - $\pm 0,3\%$ ( $\pm 1,5$ mm)	$\pm 0,2\%$
	Flatness (centre curvature / edge curvature / warpage)	ISO-10545-2	Squadro ISO 13006 - $\pm 0,4\%$ ( $\pm 1,8$ mm)	$\pm 0,35\%$
	Maximum straightness deviation, in %, in relation to the corresponding production dimensions	ISO-10545-2	Squadro ISO 13006 - $\pm 0,3\%$ ( $\pm 0,8$ mm)	$\pm 0,1\%$
	Admitted deviation, in %, of the average thickness of each tile from the production dimensions	ISO-10545-2	Squadro ISO 13006 - $\pm 5\%$ ( $\pm 0,5$ mm)	$\pm 5\%$
	Surface quality	ISO-10545-2	Il 95% min delle piastrelle deve essere esente da difetti visibili / At least 95% of the tiles must be free from visible flaws / 95% min des carreaux ne doivent présenter aucun défaut visible / Mindestens 95% der Fliesen müssen frei von sichtbaren / mín. el 95% de las baldosas tiene que estar exento de defectos visibles	CONFORME / CONFORMING / CONFORME / KONFORM / CONFORME / COOTBETCTBYET
	Amount of water absorbed, in percentage	ISO-10545-3	$E \leq 0,5\%$	average value 0,08%
	Bending strength in N/mm <sup>2</sup>	ISO-10545-4	>35 N/mm <sup>2</sup>	average value 50 N/mm <sup>2</sup>

Breaking strength in N (thickness  $\geq 7,5$ )

	mm)	ISO-10545-4	≥1300 Newton	average value 2200 N
	Resistance to abrasion of glazed tiles	ISO-10545-7	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	Cl. 3 (Amani Grey, Black deep); cl. 4 (Travertino, Marfil, Ceppo di grè)
	Resistance to abrasion of glazed tiles	ISO-10545-7	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	cl.5 (Calacatta)
	Thermal shock resistance	ISO-10545-9	Metodo di prova disponibile / Available testing method / Méthode d'essai disponible / Verfügbare Prüfmethode / Método de ensayo disponible	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Glaze crazing resistance	ISO-10545-11	Richiesta / Required / Requisite / Gefordert / Requerida	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Frost resistance	ISO-10545-12	Richiesta / Required / Requisite / Gefordert / Requerida	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Resistance to low concentrations of acids and alkali	ISO-10545-13	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	GLA Grip
	Resistance to low concentrations of acids and alkali	ISO-10545-13	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	GLA Matte
	Resistance to low concentrations of acids and alkali	ISO-10545-13	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	GLB Glossy
	Resistance to domestic chemicals and additives for swimming pools	ISO-10545-13	GB minimo / GB minimum / GB minimum / GB mindestens / GB mínimo	GA
	Resistance to staining	ISO-10545-14	classe 3 minimo / class 3 minimum / classe 3 minimum / klasse 3 mindestens / classe 3 mínimo	Cl. 3 Glossy
	Resistance to staining	ISO-10545-14	classe 3 minimo / class 3 minimum / classe 3 minimum / klasse 3 mindestens / classe 3 mínimo	Cl. 4 Matte
	Resistance to staining	ISO-10545-14	classe 3 minimo / class 3 minimum / classe 3 minimum / klasse 3 mindestens / classe 3 mínimo	Cl. 4 Grip

**Note:**

-

For optimal installation results, Florim recommends maintaining a joint of 2 mm 1/12" for single format installations and 3 mm 1/8" to combine mixed formats.